



Self-adhesive. Quality.

LFP Protec 382p

80 µm Soft-PVC monomeric, transparent glossy

Technical Product Information

Grade Characteristics

Description	Self-adhesive monomeric soft PVC, transparent glossy, 80 µm
Application	Overlaminating film with UV-absorbers to protect digital large format Inkjet-prints
Certificates	REACH conform, complies with the toys norm EN 71 part 3 and the european directive 2005/84/CE regarding phthalates in toys
Recommended application temperature	min. + 10°C
Product application temperature	- 30 to + 80°C
Durability	3 years *
Shelf life at 23°C / 50% moisture	2 years in original boxes *

Physical Properties Facestock	Value	Unit	Norm
Caliper	80 ± 5	µm	ISO 534
Stretch at break MD	> 160	%	DIN EN ISO 527
Tear resistance MD	> 26	Mpa	DIN EN ISO 527

Physical Properties Adhesive	Value	Unit	Norm
Adhesion* P3 → Permanent, clear	16 ±6	N/25mm	Finat 1

*Average value
24h auf Glas

Physical Properties Liner

HKL siliconised Kraft paper

Guarantee

INTERCOAT materials are manufactured according to highest quality standards and pass stringent quality controls prior to despatch. Any material showing an evident defect of manufacturing will be replaced promptly without charge. The wide range of different applications does not allow to test all possibilities of employment. All statements, technical information and recommendations are based on tests and practical experiences and believed to be reliable but do not constitute a guarantee or warranty. Preliminary tests are recommended for each new application. For any need of advise or technical support the INTERCOAT technical department will be pleased to assist.

* Normal storage and handling conditions. Middle-European climate conditions, unprinted.

30.09.2021

Changes without notice

AMC AG Divison Intercoat
Boschstr. 12
D-24568 Kaltenkirchen

Telefon: +49-(0)4191-8005-0
Telefax: +49-(0)4191-2450
Internet: www.Intercoat.de



ALPHASET
TECHNOLÓGIE A MATERIÁLY NA VÝROBU REKLAMY

ALPHASET spol. s r.o.
Kopčianska 19, 851 01 Bratislava
tel: +421 2 6381 2255
mobil: +421 918 656 524
e-mail: alphaset@alphaset.sk

