

JT 8500 WM-PT, PG, RT, RG

PRODUCT DESCRIPTION

Budget monomeric calendered self adhesive printing media.

Face Material: 95 µm white matt PVC

Adhesive: JT 8500 WM-PT: Emulsion acrylic permanent transparent

JT 8500 WM-PG: Emulsion acrylic permanent grey

JT 8500 WM-RT: Emulsion acrylic removable transparent

JT 8500 WM-RG: Emulsion acrylic removable grey

Liner: Clay coated 120 g/sqm

TYPICAL USE

Short -term indoor and outdoor promotional graphics on flat smooth surfaces.

PROCESSING

Especially designed for solvent based, eco-solvent, mild solvent, Latex and UV inkjet printing on wide-format printing equipment.

To achieve optimal protection and durability, JT 8500 Series needs to be laminated with LF 8500 Series.

To achieve the best possible print quality, please make sure that the correct ICC profiles or printer settings are used.

Profiles can be obtained from our subsidiaries or distributors, or can be downloaded from: www.mactacgraphics.eu.

For further information on printing, application and removal, please refer to "TB 4.1 Guidelines on handling, converting and applying Mactac Digital media".

To ensure application suitability, always test the proposed construction under actual application and end-use conditions before going into full production.

SHELF LIFE

2 years when stored at 15 to 25°C and ± 50 % relative humidity (in the original packaging).

Exposure to severe temperatures, ultraviolet light, and/or conditions in Southern European countries, tropical, sub-tropical or desert regions will cause more rapid deterioration. This also applies to polluted areas, high altitudes and south-facing exposure. No durability warranty is given for horizontal exposure.

PHYSICAL PROPERTIES (TYPICAL VALUES)

Average Values Test Method

Thickness		
Face (microns)	95 µm	ISO 534
Adhesive data, 23°C (N/25 mm)		
Peel adhesion on glass		
- Quick tack:		
JT 8500 WM-PT	12	FTM9
JT 8500 WM-PG	11	
JT 8500 WM-RT	4	
JT 8500 WM-RG	4	
- 24 hour residence:		
JT 8500 WM-PT	13	FTM1
JT 8500 WM-PG	14	
JT 8500 WM-RT	4	
JT 8500 WM-RG	3	
Dimensional stability		
Shrinkage (48 hours at 70°C applied on Aluminium)	Max. 1.0 mm	FTM14
Temperature ranges		
Minimum application temperature (°C)	+ 10°C	
Service temperature range (°C)	- 20°C to + 70°C	
Certifications		
Fire Classification	B-s1, d0	EN13501-1

EXPECTED DURABILITY

Central Europe Zone 1

Unprocessed	3 years	ISO 4892-2
Printed & laminated*	2 years	ISO 4892-2

*For more information, refer to "TB 7.5 Outdoor Durability of Mactac Graphics - Self-adhesive films".

Note : Overlamination of the inkjet-printed material delays the eventual colour fading that may occur over time. This colour fading is dependent on the quality of the inkjet inks, the orientation of the printed material, the angle of display and the exact geographical location of exposure.

ALPHASET
TECHNOLÓGIE A MATERIÁLY NA VÝROBU REKLAMY

ALPHASET spol. s r.o.
Kopčianska 19, 851 01 Bratislava
tel: +421 2 6381 2255
mobil: +421 918 656 524
e-mail: alphaset@alphaset.sk

